



TS1800™ 18oz Tarp Vinyl

SPECIFICATIONS		TEST METHOD
Composition	1650Dtex *1650 Dtex 6*6/cm warp-knitted	DIN 53830/DIN60001
	1500D *1500D 16*16/inch warp-knitted	ASTM D 751
Weight	750 gsm +/- 20gsm	DIN53352
	18oz	ASTM D 751
Laquering	/	
Surface Finish	Matte or Gloss	
Color	Yellow or upon request	
Breaking Strength (weft x warp)	2800x2500/5cm	DIN 53354
	630x563bs/2"	ASTM D 751
Tearing Strength (weft x warp)	600 x 450 N	DIN 53363
	135x100lbs/2"	ASTM D 751
Adhesion Strength	65N/5cm	DIN 53357
	15lbs/2"	ASTM D 751
Width	61"- 84"	
Fire Resistance	B1, B2,	
Temperature Resistance	NFPA-701 -30°C ~ 70°C	DIN 53372
	-20°F ~ 158°F	FS 5874

sales@kedersolutions.com

(888) 727-7050 | Fax (888) 727-7060

www.KederSolutions.com

